

Hangzhou Haikuo Rubber & Plastic Products Co., Ltd

A1005, Standford2 Building, NO.196 Zhenhua Rd, Xihu Sicence&Technology Park,
Hangzhou, China.

Test Standard: GB/T3686 - 92 GB/T10544 – 2003 MT/T98/2006

Production Name	R17	Production Date	2018-8-1		
Size	5/16	Examination Date	2018-8-02		
Operative Norm.	SAE R17				
NO.	Testing Item	Unit	Standard Request	Testing Result	Single Judgment
1	Appearance		Non-wire braided outside, Disallow bleb、Gape、Sponge、Delamination	No Flaw	OK
2	Dimension	mm	I.D.: 7.9±0.3 mm O.D.: 14.8±0.5mm	7.9 14.8	OK
3	Seal Function	Psi	Test Pressure is no less than 1.5 times of Appointed Work Pressure, Say 3000 psi, Pressure Holded 1min , without leakage and damage.	3000 psi	OK
4	Length Variation Rate	%	Under the designed Work Pressure, length of hose is no more than -4%~+2%。	-3%	OK
5	Burst Pressure	Psi	Test pressure is 4 times of Appointed pressure, Say 12000 psi , Pressure Holded 1min , Without any breakage, then rise up the pressure until breakage.	12000 psi	OK
6	Min. Bend Radius	mm		55 mm	OK
Testing Result		Meeting the criterion after Testing, hoses be allowed to shipment.			

Examination Clerk: Wang Xiu

Verification Clerk: Xing amiao